

Dexflex 911-UV

Description

Dexflex 911-UV is a 10% talc filled, UV stabilized, high impact thermoplastic olefinic elastomer (TPO) typically used for automotive exterior applications.

Availability

North America

» CustomerXpress

» Find a Sales Contact

» Request Product Information

Legend

SDS - Safety Data Sheet
PSB - Product Stewardship Bulletin

Information	SDS	Safety Summary
-------------	-----	----------------

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	22 g/10 min
Density	0.96 g/cm³
Flexural Modulus	1450 MPa
Tensile Stress at Yield	21.5 MPa
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Automotive Parts, Exterior Automotive Applications

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use
- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use