

# Hifax TRC 280X NA Black

# **Compounded Polyolefin**

#### **Product Description**

Hifax TRC 280X NA Black is a high melt flow, 31% mineral filled polypropylene copolymer for injection moulding. It combines very high flowability with an excellent impact/stiffness balance and a very low CLTE. The grade has been specifically designed for moulding of large complex parts that require high impact strength as well as good stiffness. This grade is available in pellet form. It contains no UV stabilization, and therefore it designed to be used only for fully painted parts.

## **Product Characteristics**

Status Commercial: Active

Test Method used ISO

Availability North America

Features Copolymer, High Flow, Good Impact Resistance, Good

Stiffness

**Typical Customer Applications** Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	1.14	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	20	g/10 min
Mechanical			
Tensile Stress at Yield	ISO 527-1, -2	22	MPa
Flexural modulus	ISO 178	2800	MPa
Impact			
Notched izod impact strength	ISO 180		
(23 °C, Type 1, Notch A)		10	kJ/m²
(-40 °C, Type 1, Notch A)		2.5	kJ/m²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	120	°C
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	65	°C
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinkage reco	ommendations.		

### **Notes**

Typical properties; not to be construed as specifications.