



GELOY™ Resin CR3020
Americas: COMMERCIAL

ASA, excellent weatherable, extrusion grade

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	390	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	300	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	38	%	ASTM D 638
Tensile Modulus, 5 mm/min	18700	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	580	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	18900	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	39	MPa	ISO 527
Tensile Stress, break, 50 mm/min	31	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.4	%	ISO 527
Tensile Strain, break, 50 mm/min	23	%	ISO 527
Tensile Modulus, 1 mm/min	1800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	56	MPa	ISO 178
Flexural Modulus, 2 mm/min	1800	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	0	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	0	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	45	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	3	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	100	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	74	°C	ASTM D 648



GELOY™ Resin CR3020
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	1.4E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	100	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	77	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.07	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.55 - 0.63	%	SABIC Method
Melt Flow Rate, 220°C/10.0 kgf	5	g/10 min	ASTM D 1238
Density	1.07	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	6	g/10 min	ISO 1133



GELOY™ Resin CR3020

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Profile Extrusion		
Drying Temperature	80 - 90	°C
Drying Time	3 - 6	hrs
Drying Time (Cumulative)	12	hrs
Minimum Moisture Content	0.02	%
Melt Temperature	225 - 255	°C
Barrel - Zone 1 Temperature	205 - 215	°C
Barrel - Zone 2 Temperature	215 - 230	°C
Barrel - Zone 3 Temperature	220 - 240	°C
Barrel - Zone 4 Temperature	225 - 245	°C
Adapter Temperature	225 - 245	°C
Die Temperature	225 - 245	°C
Calibrator Temperature	15 - 65	°C

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES (SELLER) ARE SOLD SUBJECT TO SELLER S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller s materials, products, services or recommendations for the user s particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller s Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

©2016Saudi Basic Industries Corporation (SABIC).