



GELOY™ Resin CR8510
Americas: COMMERCIAL

ASA, excellent weatherability, injection molding.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	400	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	330	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	60	%	ASTM D 638
Tensile Modulus, 50 mm/min	21100	kgf/cm ²	ASTM D 638
Tensile Modulus, 5 mm/min	20000	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	690	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	22100	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	93	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	43	MPa	ISO 527
Tensile Stress, break, 50 mm/min	35	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.3	%	ISO 527
Tensile Strain, break, 50 mm/min	19	%	ISO 527
Tensile Modulus, 1 mm/min	2040	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	64	MPa	ISO 178
Flexural Modulus, 2 mm/min	2060	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	40	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	6	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	305	cm-kgf	ASTM D 3763
Instrumented Impact Total Energy, -30°C	40	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A



GELOY™ Resin CR8510
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	98	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	103	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	90	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.4E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, approximate maximum	98	°C	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	105	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	88	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	89	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.8	%	SABIC Method
Melt Flow Rate, 220°C/10.0 kgf	6.3	g/10 min	ASTM D 1238
Melt Flow Rate, 260°C/5.0 kgf	11	g/10 min	ASTM D 1238
Melt Flow Rate, 280°C/3.8 kgf	7.8	g/10 min	ASTM D 1238
Density	1.07	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62



GELOY™ Resin CR8510
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Melt Volume Rate, MVR at 220°C/10.0 kg	6	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	10	cm ³ /10 min	ISO 1133
OPTICAL			
Gloss, untextured, 60 degrees	94	-	ASTM D 523
ELECTRICAL			
Dissipation Factor, 100 kHz	0.018	-	ASTM D 150
Dissipation Factor, 1 MHz	0.026	-	ASTM D 150
Dielectric Strength in oil, 1.5mm	26.1	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C



GELOY™ Resin CR8510
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	85 - 90	°C
Drying Time	4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	240 - 270	°C
Nozzle Temperature	220 - 255	°C
Front - Zone 3 Temperature	230 - 260	°C
Middle - Zone 2 Temperature	220 - 255	°C
Rear - Zone 1 Temperature	215 - 250	°C
Mold Temperature	60 - 85	°C
Back Pressure	0.3 - 1	MPa
Screw Speed	30 - 80	rpm
Shot to Cylinder Size	40 - 80	%
Vent Depth	0.038 - 0.076	mm