

SABIC[®] PPCOMPOUND 3720E

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

SABIC[®] PPcompound 3720E is a mineral filled modified polypropylene. Material properties include an excellent stiffness and impact ratio with a low emission and fogging behaviour. Typical applications include non esthetical automotive interior parts.

SABIC[®] PPcompound 3720E is a designated automotive grade.

IMDS ID: 96146063

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt flow rate (MFR)			
at 230 °C and 2.16 kg	18	dg/min	ISO 1133
Density ⁽¹⁾	1040	kg/m ³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	1.1	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile test			
Tensile modulus	2000	MPa	ISO 527/1A
stress at yield	28	MPa	ISO 527/1A
stress at break	25	MPa	ISO 527/1A
strain at break	45	%	ISO 527/1A
Flexural test			
Flexural modulus	2200	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	6	kJ/m ²	ISO 180/1A
at 0 °C	3.5	kJ/m ²	ISO 180/1A
at -20 °C	3	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	110	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	95	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.