

SABIC® VESTOLEN P 9421 67727 GREY

PP RANDOM COPOLYMER

DESCRIPTION

This random copolymer has a high molecular weight with properties required for high demanding pressure pipes. It is highly heat stabilised and especially formulated for extraction resistance. This grade with long service life is used for the manufacturing of cold and hot water pipes and fittings for transport of drinking water. This grade fulfills the requirements in EN ISO 15874, ISO 3213, DIN 8078 and DIN 8077. It also complies with German regulations for materials in contact with water intended for human consumption (BGA requirements and KTW recommendations). Health, Safety and Food Contact regulations: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>. The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications. IMDS 80775790

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	0.30	dg/min	ISO 1133
at 190 °C and 5 kg	0.50	dg/min	ISO 1133

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.