

SABIC® STAMAX™ 40YM243

PP LGF REINFORCED

DESCRIPTION

SABIC® STAMAX 40YM243 is a 40% long glass fiber reinforced UV stabilised grade. The glass fibres are chemically coupled to the PP matrix, resulting in high stiffness and strength.

IMDS ID: 120207048

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-------------------|--------------|
| POLYMER PROPERTIES | | | |
| Density | 1220 | kg/m ³ | ISO 1183 |
| Glass fibre content | 40 | % | ISO 3451 |
| MECHANICAL PROPERTIES (1) | | | |
| Tensile modulus | | | |
| at 23 °C | 8200 | MPa | ISO 527/1A |
| at 80 °C | 5400 | MPa | ISO 527/1A |
| Tensile strength | | | |
| at 23 °C | 110 | MPa | ISO 527/1A |
| at 80 °C | 65 | MPa | ISO 527/1A |
| Tensile elongation at break | | | |
| at 23 °C | 2.1 | % | ISO 527/1A |
| Flexural Modulus | | | |
| at 23 °C | 8700 | MPa | ISO 178 |
| at 80 °C | 6100 | MPa | ISO 178 |
| Flexural strength | | | |
| at 23 °C | 180 | MPa | ISO 178 |
| at 80 °C | 105 | MPa | ISO 178 |
| Charpy Impact Strength Notched | | | |
| at 23 °C | 26 | kJ/m ² | ISO 179/1eA |
| at -30 °C | 25 | kJ/m ² | ISO 179/1eA |
| Charpy impact unnotched | | | |
| at 23 °C | 55 | kJ/m ² | ISO 179/1eU |
| at -30 °C | 50 | kJ/m ² | ISO 179/1eU |
| THERMAL PROPERTIES | | | |
| Heat deflection temperature | | | |
| at 1.80 MPa (HDT/A) | 158 | °C | ISO 75/A |
| Coeff. of linear thermal expansion | | | |
| -30 °C to 100 °C | 40 | µm/mK | ISO 11359-2 |

(1) All measurements on injection molded samples.