



LNP™ LUBRILOY™ Compound UX98388

Americas: COMMERCIAL

Also known as: LNP™ LUBRILOY™ Compound PDX-U-98388

Product reorder name: UX98388

LNP LUBRILOY™ UX98388 is a compound based on Polyphthalamide resin containing Proprietary Lubricant. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	72	MPa	ISO 527
Tensile Stress, yield, 5 mm/min	78	MPa	ISO 527
Tensile Stress, break, 5 mm/min	67	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6.1	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	106	MPa	ISO 178
Flexural Modulus	2500	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, xflow	9.1E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	131	°C	ISO 75/Bf
PHYSICAL			
Mold Shrinkage, flow (5)	2.5	%	SABIC Method
Mold Shrinkage, flow, 24 hrs (5)	1.6	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.6	%	ISO 294
Density	1.12	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.34	%	ISO 62-1



LNP™ LUBRILOY™ Compound UX98388

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15	%
Melt Temperature	315 - 330	°C
Front - Zone 3 Temperature	325 - 340	°C
Middle - Zone 2 Temperature	315 - 325	°C
Rear - Zone 1 Temperature	310 - 320	°C
Mold Temperature	150 - 170	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm