



LNP™ THERMOCOMP™ Compound UF006AS

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound UF-1006 A HS

Product reorder name: UF006AS

LNP THERMOCOMP™ UF006AS is a compound based on Polyphthalamide resin containing 30% Glass Fiber. Added features of this material include: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1860	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	118300	kgf/cm ²	ASTM D 638
Flexural Stress	2590	kgf/cm ²	ASTM D 790
Flexural Modulus	117600	kgf/cm ²	ASTM D 790
Tensile Stress, break	167	MPa	ISO 527
Tensile Strain, break	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	14790	MPa	ISO 527
Flexural Stress	255	MPa	ISO 178
Flexural Modulus	11220	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	41	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	101	cm-kgf	ASTM D 3763
Multiaxial Impact	15	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	282	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	260	°C	ISO 75/Af
PHYSICAL			
Density	1.454	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.22	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2	%	ASTM D 955



LNP™ THERMOCOMP™ Compound UF006AS

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, xflow, 24 hrs (5)	1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.24	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.97	%	ISO 294
Density	1.45	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.41	%	ISO 62



LNP™ THERMOCOMP™ Compound UF006AS

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15	%
Melt Temperature	315 - 330	°C
Front - Zone 3 Temperature	325 - 340	°C
Middle - Zone 2 Temperature	315 - 325	°C
Rear - Zone 1 Temperature	310 - 320	°C
Mold Temperature	140 - 165	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm