



LNP™ THERMOCOMP™ Compound UF008AR

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound UF-1008 A MR

Product reorder name: UF008AR

LNP THERMOCOMP UF008AR is a compound based on Polyphthalamide resin, containing Glass Fiber. Added features include; Mold Release.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	234	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	14500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	315	MPa	ISO 178
Flexural Modulus, 2 mm/min	12000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	55	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	2.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.3E-05	1/°C	ISO 11359-2
PHYSICAL			
Mold Shrinkage, flow (5)	0.14	%	SABIC Method
Density	1.53	g/cm ³	ISO 1183