



## LNP™ LUBRICOMP™ Compound KL002L

### Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound KL-4020 LE

Product reorder name: KL002L

LNP LUBRICOMP KL002L is a compound based on Acetal Copolymer resin containing 10% PTFE. Added features of this grade include: Wear Resistant, Low Extractible.

| TYPICAL PROPERTIES <sup>1</sup>              | TYPICAL VALUE | Unit                | Standard    |
|----------------------------------------------|---------------|---------------------|-------------|
| <b>MECHANICAL</b>                            |               |                     |             |
| Tensile Stress, brk, Type I, 5 mm/min        | 480           | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Strain, brk, Type I, 5 mm/min        | 9.7           | %                   | ASTM D 638  |
| Tensile Modulus, 50 mm/min                   | 26000         | kgf/cm <sup>2</sup> | ASTM D 638  |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 690           | kgf/cm <sup>2</sup> | ASTM D 790  |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 24100         | kgf/cm <sup>2</sup> | ASTM D 790  |
| <b>IMPACT</b>                                |               |                     |             |
| Izod Impact, unnotched, 23°C                 | 57            | cm-kgf/cm           | ASTM D 4812 |
| Izod Impact, notched, 23°C                   | 5             | cm-kgf/cm           | ASTM D 256  |
| <b>THERMAL</b>                               |               |                     |             |
| HDT, 1.82 MPa, 3.2mm, unannealed             | 92            | °C                  | ASTM D 648  |
| <b>PHYSICAL</b>                              |               |                     |             |
| Density                                      | 1.45          | g/cm <sup>3</sup>   | ASTM D 792  |



## LNP™ LUBRICOMP™ Compound KL002L

Americas: COMMERCIAL

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 80            | °C   |
| Drying Time                 | 4             | hrs  |
| Melt Temperature            | 200 - 215     | °C   |
| Front - Zone 3 Temperature  | 210 - 220     | °C   |
| Middle - Zone 2 Temperature | 195 - 205     | °C   |
| Rear - Zone 1 Temperature   | 175 - 190     | °C   |
| Mold Temperature            | 80 - 110      | °C   |
| Back Pressure               | 0.2 - 0.3     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |