

LNP* Lubricomp* Compound KL004XXC

Asia Pacific: COMMERCIAL

Also known as: LNP* Lubricomp* Compound KL-4040

Product reorder name: KL004XXC

LNP LUBRICOMP* KL004XXC is a compound based on Acetal Copolymer resin containing PTFE. Added features of this material include: Internally Lubricated.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yield	520	kgf/cm ²	ASTM D 638
Tensile Stress, break	510	kgf/cm ²	ASTM D 638
Tensile Strain, yield	11.2	%	ASTM D 638
Tensile Strain, break	17.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	21700	kgf/cm ²	ASTM D 638
Flexural Stress	770	kgf/cm ²	ASTM D 790
Flexural Modulus	21000	kgf/cm ²	ASTM D 790
Tensile Stress, yield	47	MPa	ISO 527
Tensile Stress, break	46	MPa	ISO 527
Tensile Strain, yield	9.6	%	ISO 527
Tensile Strain, break	22.7	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress	79	MPa	ISO 178
Flexural Modulus	2600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	66	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	65	cm-kgf	ASTM D 3763
Multiaxial Impact	7	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	157	°C	ASTM D 648

LNP* Lubricomp* Compound KL004XXC

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	99	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.1E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.11E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	1.1E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.11E-04	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	98	°C	ISO 75/Af
PHYSICAL			
Density	1.5	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.15	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	1.97 - 2.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1.97 - 2.5	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	1.97 - 2.5	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	1.97 - 2.5	%	ISO 294
Wear Factor Washer	10	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.3	-	ASTM D 3702 Modified
Static COF	0.18	-	ASTM D 3702 Modified
Density	1.5	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.26	%	ISO 62

LNP* Lubricomp* Compound KL004XXC

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	200 - 215	°C
Front - Zone 3 Temperature	210 - 220	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm