



LNP™ STAT-KON™ Compound KD000EI

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound K-HI NAT
Product reorder name: KD000EI

LNP STAT-KON KD000EI is a compound based on Acetal Copolymer resin containing Carbon Powder. Added features include: Electrically Conductive, Impact Modified.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	34	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	7.9	%	ISO 527
Tensile Modulus, 1 mm/min	1700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	45	MPa	ISO 178
Flexural Modulus, 2 mm/min	1700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	7.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.7E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	123	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	67	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	2.1	%	SABIC Method
Density	1.42	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	1	%	ISO 62-1
ELECTRICAL			
Surface Resistivity	1.E+03 - 1.E+05	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating (3)(4)	3	mm	UL 94 by SABIC-IP



LNP™ STAT-KON™ Compound KD000EI
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	200 - 215	°C
Front - Zone 3 Temperature	210 - 220	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm