



LNP™ THERMOCOMP™ Compound KF008

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound KFX-1008

Product reorder name: KF008

LNP THERMOCOMP KF008 is a compound based on Acetal Copolymer resin containing Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	131	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Flexural Stress, yield, 2 mm/min	179	MPa	ISO 178
Flexural Modulus, 2 mm/min	9600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	4.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.6E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	164	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.3 - 0.7	%	SABIC Method
Density	1.7	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0	%	ISO 62-1



LNP™ THERMOCOMP™ Compound KF008

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	200 - 215	°C
Front - Zone 3 Temperature	210 - 220	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm