



LNP™ STAT-KON™ Compound KE004

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound KC-1004

Product reorder name: KE004

LNP STAT-KON KE004 is a compound based on Acetal Copolymer resin containing 20% Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	1230	kgf/cm ²	ASTM D 638
Tensile Stress, break	1230	kgf/cm ²	ASTM D 638
Tensile Strain, yield	1.6	%	ASTM D 638
Tensile Strain, break	1.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	147600	kgf/cm ²	ASTM D 638
Flexural Stress	1540	kgf/cm ²	ASTM D 790
Flexural Modulus	112400	kgf/cm ²	ASTM D 790
Tensile Stress, yield	110	MPa	ISO 527
Tensile Stress, break	110	MPa	ISO 527
Tensile Strain, yield	1.4	%	ISO 527
Tensile Strain, break	1.4	%	ISO 527
Tensile Modulus, 1 mm/min	12990	MPa	ISO 527
Flexural Stress	160	MPa	ISO 178
Flexural Modulus	11500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	43	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	111	cm-kgf	ASTM D 3763
Multiaxial Impact	25	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	162	°C	ASTM D 648



LNP™ STAT-KON™ Compound KE004

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	160	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.84E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.06E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.9E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	3.1E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	163	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Af
PHYSICAL			
Density	1.47	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.2	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.6 - 1.8	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.69	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.7	%	ISO 294
Density	1.47	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+06	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound KE004

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	200 - 215	°C
Front - Zone 3 Temperature	210 - 220	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm