



LNP™ STAT-KON™ Compound KEP33

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound KCL-4533

Product reorder name: KEP33

LNP STAT-KON™ KEP33 is a compound based on Acetal resin containing 15% Carbon Fiber, 15% PTFE/Silicone. Added features of this material include: Electrically Conductive, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	790	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	104000	kgf/cm ²	ASTM D 638
Flexural Stress	1160	kgf/cm ²	ASTM D 790
Flexural Modulus	72900	kgf/cm ²	ASTM D 790
Tensile Stress, break	74	MPa	ISO 527
Tensile Strain, break	1	%	ISO 527
Tensile Modulus, 1 mm/min	10170	MPa	ISO 527
Flexural Stress	106	MPa	ISO 178
Flexural Modulus	8270	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	13	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	3	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	73	cm-kgf	ASTM D 3763
Multiaxial Impact	41	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	66	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	155	°C	ISO 75/Af
PHYSICAL			
Density	1.473	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.21	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.4 - 0.6	%	ASTM D 955



LNP™ STAT-KON™ Compound KEP33

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, xflow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.4 - 0.6	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.7 - 0.9	%	ISO 294
Wear Factor Washer	202	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.36	-	ASTM D 3702 Modified
Static COF	0.31	-	ASTM D 3702 Modified
Density	1.46	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.32	%	ISO 62
ELECTRICAL			
Volume Resistivity	1.E+01 - 1.E+04	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+01 - 1.E+04	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound KEP33

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	200 - 215	°C
Front - Zone 3 Temperature	210 - 220	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	175 - 190	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm