



## LNP™ STAT-LOY™ Compound P3000U

### Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-LOY™ Compound P-UV NAT

Product reorder name: P3000U

LNP STAT-KON P3000U is a compound based on PA 6 resin. Added features include; Antistatic, UV - Stabilized.

| TYPICAL PROPERTIES <sup>1</sup>        | TYPICAL VALUE   | Unit              | Standard     |
|----------------------------------------|-----------------|-------------------|--------------|
| <b>MECHANICAL</b>                      |                 |                   |              |
| Tensile Stress, yield, 50 mm/min       | 56              | MPa               | ISO 527      |
| Tensile Stress, break, 50 mm/min       | 44              | MPa               | ISO 527      |
| Tensile Strain, yield, 50 mm/min       | 3.6             | %                 | ISO 527      |
| Flexural Stress, yield, 2 mm/min       | 59              | MPa               | ISO 178      |
| Flexural Modulus, 2 mm/min             | 1800            | MPa               | ISO 178      |
| <b>IMPACT</b>                          |                 |                   |              |
| Izod Impact, unnotched 80*10*4 +23°C   | NB              | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C     | 9               | kJ/m <sup>2</sup> | ISO 180/1A   |
| <b>THERMAL</b>                         |                 |                   |              |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 162             | °C                | ISO 75/Bf    |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm  | 55              | °C                | ISO 75/Af    |
| <b>PHYSICAL</b>                        |                 |                   |              |
| Mold Shrinkage, flow (5)               | 0.8             | %                 | SABIC Method |
| Density                                | 1.17            | g/cm <sup>3</sup> | ISO 1183     |
| Water Absorption, 23°C/24hrs           | 6.3             | %                 | ISO 62-1     |
| <b>ELECTRICAL</b>                      |                 |                   |              |
| Surface Resistivity                    | 1.E+10 - 1.E+12 | Ohm               | ASTM D 257   |



**LNP™ STAT-LOY™ Compound P3000U**  
**Europe-Africa-Middle East: COMMERCIAL**

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 80            | °C   |
| Drying Time                 | 4             | hrs  |
| Maximum Moisture Content    | 0.15 - 0.25   | %    |
| Melt Temperature            | 265 - 275     | °C   |
| Front - Zone 3 Temperature  | 275 - 290     | °C   |
| Middle - Zone 2 Temperature | 265 - 275     | °C   |
| Rear - Zone 1 Temperature   | 250 - 260     | °C   |
| Mold Temperature            | 80 - 95       | °C   |
| Back Pressure               | 0.3 - 0.7     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |