



LNP™ STAT-KON™ Compound PFD04S

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound STAT-KON-PF
Product reorder name: PFD04S

LNP STAT-KON PFD04S is a compound based on PA 6 resin containing Glass Fiber, Carbon Powder. Added features include: Electrically Conductive, Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	107	MPa	ISO 527
Tensile Stress, break, 5 mm/min	87	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	7000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	152	MPa	ISO 178
Flexural Stress, break, 2 mm/min	136	MPa	ISO 178
Flexural Modulus, 2 mm/min	5900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	50	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	3.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.12E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	214	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	195	°C	ISO 75/Af
Relative Temp Index, Elec	65	°C	UL 746B
Relative Temp Index, Mech w/impact	65	°C	UL 746B
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.4 - 0.6	%	SABIC Method
Mold Shrinkage, flow (5)	0.4 - 0.6	%	SABIC Method
Density	1.32	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	1	%	ISO 62-1
ELECTRICAL			
Surface Resistivity	1.E+04 - 1.E+06	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1	mm	UL 94



LNP™ STAT-KON™ Compound PFD04S
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm