



LNP™ LUBRICOMP™ Compound PFP36

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound PFL-4536

Product reorder name: PFP36

LNP LUBRICOMP PFL36 is a compound based on Nylon 6 resin containing 30% Glass Fiber, 15% PTFE/Silicone. Added features of this grade include: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	55	MPa	ISO 527
Tensile Strain, break	6 - 8	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress	80	MPa	ISO 178
Flexural Modulus	3100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	100	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	58	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow, 24 hrs (5)	1.2 - 1.4	%	ISO 294
Density	1.22	g/cm ³	ISO 1183



LNP™ LUBRICOMP™ Compound PFP36

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	255 - 265	°C
Front - Zone 3 Temperature	250 - 260	°C
Middle - Zone 2 Temperature	250 - 260	°C
Rear - Zone 1 Temperature	245 - 255	°C
Mold Temperature	55 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm