



LNP™ STAT-KON™ Compound PX05047

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PC
Product reorder name: PX05047

LNP STAT-KON PX05047 is a compound based on PA 6 resin containing Carbon Fiber, Proprietary Filler (s). Added features include: Electrically Conductive, High Impact.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	114	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.6	%	ISO 527
Flexural Stress, break, 2 mm/min	159	MPa	ISO 178
Flexural Modulus, 2 mm/min	6000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	50	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.09E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.15E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	214	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	190	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.2 - 0.4	%	SABIC Method
Density	1.17	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	1.5	%	ISO 62-1
ELECTRICAL			
Surface Resistivity	1.E+03 - 1.E+05	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound PX05047
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm