



LNP™ THERMOTUF™ Compound PF00AIS

Americas: COMMERCIAL

Also known as: LNP™ THERMOTUF™ Compound PF-100-10 HI HS

Product reorder name: PF00AIS

LNP THERMOTUF™ PF00AIS is a compound based on Nylon 6 resin containing 50% Glass Fiber. Added features of this material include: Heat Stabilized, High Impact.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1530	kgf/cm ²	ASTM D 638
Flexural Stress	2530	kgf/cm ²	ASTM D 790
Flexural Modulus	125100	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	132	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	16	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	204	°C	ASTM D 648
PHYSICAL			
Density	1.63	g/cm ³	ASTM D 792



LNP™ THERMOTUF™ Compound PF00AIS

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm