



LNP™ THERMOCOMP™ Compound PFW64

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound PFM-3264

Product reorder name: PFW64

LNP THERMOCOMP PFW64 is a compound based on Nylon 6 resin containing 20% Glass Fiber, 30% Wollastonite.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1370	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 50 mm/min	125400	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1720	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	94100	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	133	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	11480	MPa	ISO 527
Flexural Stress	195	MPa	ISO 178
Flexural Modulus, 2 mm/min	10620	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	82	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	0	cm-kgf/cm	ASTM D 256
Multiaxial Impact	29	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	75	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	39	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	216	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	203	°C	ASTM D 648
CTE, -30°C to 30°C, flow	3.37E+01	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.25E+01	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	218	°C	ISO 75/Bf



LNP™ THERMOCOMP™ Compound PFW64

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	201	°C	ISO 75/Af
PHYSICAL			
Density	1.63	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.75	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.8 - 1	%	ASTM D 955
Density	1.63	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.98	%	ISO 62



LNP™ THERMOCOMP™ Compound PFW64

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm