



LNP™ STAT-LOY™ Compound PF306

Americas: COMMERCIAL

Also known as: LNP™ STAT-LOY™ Compound PF-30

Product reorder name: PF306

LNP STAT-LOY PF306 is a compound based on Nylon 6 resin containing 30% Glass Fiber. Added feature of this grade includes: Antistat.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	950	kgf/cm ²	ASTM D 638
Tensile Stress, break	950	kgf/cm ²	ASTM D 638
Tensile Strain, yield	2.7	%	ASTM D 638
Tensile Strain, break	2.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	77300	kgf/cm ²	ASTM D 638
Flexural Stress	980	kgf/cm ²	ASTM D 790
Flexural Modulus	56200	kgf/cm ²	ASTM D 790
Tensile Stress, yield	83	MPa	ISO 527
Tensile Stress, break	83	MPa	ISO 527
Tensile Strain, yield	2.7	%	ISO 527
Tensile Strain, break	2.8	%	ISO 527
Tensile Modulus, 1 mm/min	7470	MPa	ISO 527
Flexural Stress	106	MPa	ISO 178
Flexural Modulus	6000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	97	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	10	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	173	cm-kgf	ASTM D 3763
Multiaxial Impact	61	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	202	°C	ASTM D 648



LNP™ STAT-LOY™ Compound PF306

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	185	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.19E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.96E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	1.19E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	201	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	182	°C	ISO 75/Af
PHYSICAL			
Density	1.39	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	5.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.28	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.82	%	ISO 294
Density	1.39	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	9.E+00 - 1.1E+01	Ohm	ASTM D 257



LNP™ STAT-LOY™ Compound PF306

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm