



LNP™ LUBRICOMP™ Compound AG5LT2

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound AG5LT2

Product reorder name: AG5LT2

LNP* LUBRICOMP* AG5LT2 Is a compound based on PA66 resin, containing Glass Fiber and PTFE. Added features include: Internally Lubricated

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	168	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.4	%	ISO 527
Tensile Modulus, 1 mm/min	9500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	234	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3.7	%	ISO 178
Flexural Modulus, 2 mm/min	7900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	55	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	2.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.9E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	259	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	246	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.2 - 0.4	%	SABIC Method
Wear Factor Washer	11	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Instr.
Dynamic COF	0.42	-	ASTM D 3702 Modified: Instr.
Static COF	0.35	-	ASTM D 3702 Modified: Instr.
Density	1.4	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.74	%	ISO 62-1



LNP™ LUBRICOMP™ Compound AG5LT2

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm