



LNP™ LUBRICOMP™ Compound RFP36

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound RFL-4536

Product reorder name: RFP36

LNP LUBRICOMP RFP36 is a compound based on Nylon 66 resin containing 30% Glass Fiber, 15% PTFE, Silicone. Added features of this material include: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Modulus, 50 mm/min	106800	kgf/cm ²	ASTM D 638
Flexural Stress	1980	kgf/cm ²	ASTM D 790
Flexural Modulus	77200	kgf/cm ²	ASTM D 790
Tensile Modulus, 1 mm/min	9800	MPa	ISO 527
IMPACT			
Izod Impact, unnotched, 23°C	79	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	14	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	71	cm-kgf	ASTM D 3763
Multiaxial Impact	50	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	50	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	233	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	236	°C	ISO 75/Af
PHYSICAL			
Density	1.48	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.78	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.21	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.97	%	ISO 294
Wear Factor Washer	11	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.56	-	ASTM D 3702 Modified
Static COF	0.48	-	ASTM D 3702 Modified



LNP™ LUBRICOMP™ Compound RFP36

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Density	1.48	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.22	%	ISO 62
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



LNP™ LUBRICOMP™ Compound RFP36

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm