

LNP* Lubricomp* Compound RFM62

Asia Pacific: COMMERCIAL

Also known as: LNP* Lubricomp* Compound RFM-3362

Product reorder name: RFM62

LNP* Lubricomp* RFM62 is a compound based on Nylon 66 resin containing Glass Fiber, Mineral.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, break	1050	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.1	%	ASTM D 638
Flexural Stress	1610	kgf/cm ²	ASTM D 790
Flexural Modulus	84200	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	3	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	2	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	245	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	236	°C	ASTM D 648
PHYSICAL			
Density	1.48	g/cm ³	ASTM D 792