



LNP™ LUBRICOMP™ Compound RX01514

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound PDX-R-01514

Product reorder name: RX01514

LNP LUBRICOMP RX01514 is a compound based on Nylon 66 resin containing Proprietary Filler(s). Added feature of this material is: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	860	kgf/cm ²	ASTM D 638
Tensile Stress, break	730	kgf/cm ²	ASTM D 638
Tensile Strain, yield	4.2	%	ASTM D 638
Tensile Strain, break	21.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	35100	kgf/cm ²	ASTM D 638
Flexural Modulus	28100	kgf/cm ²	ASTM D 790
Tensile Stress, yield	80	MPa	ISO 527
Tensile Stress, break	78	MPa	ISO 527
Tensile Strain, yield	3.9	%	ISO 527
Tensile Strain, break	19.1	%	ISO 527
Tensile Modulus, 1 mm/min	3400	MPa	ISO 527
Flexural Stress	96	MPa	ISO 178
Flexural Modulus	2800	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	193	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	296	cm-kgf	ASTM D 3763
Multiaxial Impact	489	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	251	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	183	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	66	°C	ASTM D 648



LNP™ LUBRICOMP™ Compound RX01514

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	8.28E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.64E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.7E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	156	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	62	°C	ISO 75/Af
PHYSICAL			
Density	1.15	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	1.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	1 - 1.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.2 - 1.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	1.1	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.3	%	ISO 294
Wear Factor Washer	67	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.81	-	ASTM D 3702 Modified
Static COF	0.62	-	ASTM D 3702 Modified
Density	1.14	g/cm ³	ISO 1183



LNP™ LUBRICOMP™ Compound RX01514

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	275 - 290	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm