



LNP™ LUBRICOMP™ Compound RL4040HSUV

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound RL-4040 HS UV

Product reorder name: RL4040HSUV

LNP* LUBRICOMP* RL4040HSUV is a compound based on Nylon 66 containing 20% PTFE. Added features of this grade include: Heat Stabilized, UV Stabilized, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	650	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	650	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	5.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	7.9	%	ASTM D 638
Tensile Modulus, 5 mm/min	29400	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	26900	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	63	MPa	ISO 527
Tensile Stress, break, 5 mm/min	63	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5.1	%	ISO 527
Tensile Strain, break, 5 mm/min	9.6	%	ISO 527
Tensile Modulus, 1 mm/min	2790	MPa	ISO 527
Flexural Stress	97	MPa	ISO 178
Flexural Modulus, 2 mm/min	2550	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	69	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Multiaxial Impact	8	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	44	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	42	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	236	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	64	°C	ASTM D 648



LNP™ LUBRICOMP™ Compound RL4040HSUV

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -30°C to 30°C, flow	1.12E-04	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	9.2E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	102	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	62	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.28	-	ASTM D 792
Density	1.274	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.75	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	1 - 3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Wear Factor Washer	28	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Wear Factor Ring	0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.22	-	ASTM D 3702 Modified: Manual
Static COF	0.11	-	ASTM D 3702 Modified: Manual
Moisture Absorption (23°C / 50% RH)	1.1	%	ISO 62



LNP™ LUBRICOMP™ Compound RL4040HSUV

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	275 - 290	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm