



LNP™ LUBRICOMP™ Compound RFP36L

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound RFL-4536 LE

Product reorder name: RFP36L

LNP™ LUBRICOMP™ RFP36L is a compound based on Nylon 66 resin containing 30% Glass Fiber, 15% PTFE/Silicone. Added features of this grade include: Low Extractable, Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1520	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.3	%	ASTM D 638
Tensile Modulus, 5 mm/min	104200	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2230	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	98500	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	150	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	10310	MPa	ISO 527
Flexural Stress	214	MPa	ISO 178
Flexural Modulus, 2 mm/min	9140	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	76	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	10	cm-kgf/cm	ASTM D 256
Multiaxial Impact	22	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	76	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	52	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	261	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	253	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.5E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	5.6E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	259	°C	ISO 75/Bf



LNP™ LUBRICOMP™ Compound RFP36L

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	249	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.44	-	ASTM D 792
Density	1.435	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.69	%	ASTM D 570
Mold Shrinkage, xflow (5)	1.5	%	SABIC Method
Mold Shrinkage, flow, 24 hrs (5)	0.6	%	ASTM D 955
Wear Factor Washer	27	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Wear Factor Ring	3	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.52	-	ASTM D 3702 Modified
Static COF	0.5	-	ASTM D 3702 Modified
Moisture Absorption (23°C / 50% RH)	0.47	%	ISO 62



LNP™ LUBRICOMP™ Compound RFP36L

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm