



LNP™ STAT-KON™ Compound RE002

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound RC-1002

Product reorder name: RE002

LNP STAT-KON RE002 is a compound based on Nylon 66 resin containing 10% Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	1370	kgf/cm ²	ASTM D 638
Tensile Stress, break	1290	kgf/cm ²	ASTM D 638
Tensile Strain, yield	2.3	%	ASTM D 638
Tensile Strain, break	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	84300	kgf/cm ²	ASTM D 638
Flexural Stress	2100	kgf/cm ²	ASTM D 790
Flexural Modulus	70300	kgf/cm ²	ASTM D 790
Tensile Stress, yield	131	MPa	ISO 527
Tensile Stress, break	131	MPa	ISO 527
Tensile Strain, yield	2.1	%	ISO 527
Tensile Strain, break	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	7800	MPa	ISO 527
Flexural Stress	191	MPa	ISO 178
Flexural Modulus	6000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	37	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	2	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	60	cm-kgf	ASTM D 3763
Multiaxial Impact	18	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	24	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	258	°C	ASTM D 648



LNP™ STAT-KON™ Compound RE002

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	245	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.28E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.88E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.9E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	254	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	241	°C	ISO 75/Af
PHYSICAL			
Density	1.18	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.8	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.74	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.3	%	ISO 294
Density	1.18	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+01 - 1.E+03	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound RE002

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm