



LNP™ STAT-KON™ Compound RC008

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound RC1008

Product reorder name: RC008

LNP STAT-KON RC008 is a compound based on Nylon 66 resin containing Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	260	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	27400	MPa	ISO 527
Flexural Stress, break, 2 mm/min	358	MPa	ISO 178
Flexural Modulus, 2 mm/min	23300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	56	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	7.E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.8E-05	1/°C	ISO 11359-2
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	252	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	260	°C	ISO 75/Bf
PHYSICAL			
Density	1.32	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+01 - 1.E+03	Ohm	ASTM D 257
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94



LNP™ STAT-KON™ Compound RC008
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	255 - 290	°C
Front - Zone 3 Temperature	260 - 270	°C
Middle - Zone 2 Temperature	255 - 265	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	40 - 65	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm