



LNP™ STAT-KON™ Compound RX08408

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound RX08408

Product reorder name: RX08408

LNP STAT-KON RX08404 is a compound based on Nylon 66 containing Carbon Powder. Added features of this material include: Electrically Conductive, High Impact.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	460	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	26	%	ASTM D 638
Tensile Modulus, 50 mm/min	19900	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	17900	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	47	MPa	ISO 527
Tensile Strain, break, 5 mm/min	26	%	ISO 527
Tensile Modulus, 1 mm/min	1930	MPa	ISO 527
Flexural Stress	61	MPa	ISO 178
Flexural Modulus, 2 mm/min	1850	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	175	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	14	cm-kgf/cm	ASTM D 256
Multiaxial Impact	254	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	224	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	196	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	195	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	60	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.1E-04	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	1.14E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	117	°C	ISO 75/Af



LNP™ STAT-KON™ Compound RX08408

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Moisture Absorption, 50% RH, 24 hrs	0.6	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	3 - 5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	3 - 5	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.87	%	ISO 62
ELECTRICAL			
Volume Resistivity	1.E+03 - 1.E+06	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+03 - 1.E+06	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound RX08408

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm