



LNP™ THERMOCOMP™ Compound RF004XXD

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-1004

Product reorder name: RF004XXD

LNP THERMOCOMP™ RF004XXD is a compound based on Nylon 66 resin containing 20% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1590	kgf/cm ²	ASTM D 638
Tensile Strain, break	3.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	73100	kgf/cm ²	ASTM D 638
Flexural Stress	2350	kgf/cm ²	ASTM D 790
Flexural Modulus	59700	kgf/cm ²	ASTM D 790
Tensile Stress, break	159	MPa	ISO 527
Tensile Strain, break	3.7	%	ISO 527
Tensile Modulus, 1 mm/min	7300	MPa	ISO 527
Flexural Stress	241	MPa	ISO 178
Flexural Modulus	7000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	84	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	10	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	116	cm-kgf	ASTM D 3763
Multiaxial Impact	25	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	56	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	260	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	247	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.78E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.92E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.88E-05	1/°C	ISO 11359-2



LNP™ THERMOCOMP™ Compound RF004XXD

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, xflow	7.94E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	221	°C	ISO 75/Af
PHYSICAL			
Density	1.295	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.8	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.2	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.47	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.24	%	ISO 294
Wear Factor Washer	80	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.68	-	ASTM D 3702 Modified
Static COF	0.52	-	ASTM D 3702 Modified
Density	1.29	g/cm ³	ISO 1183



LNP™ THERMOCOMP™ Compound RF004XXD

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm