



LNP™ THERMOCOMP™ Compound RF006ESZ

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-1006 EM HS

Product reorder name: RF006ESZ

LNP THERMOCOMP™ RF006ESZ is a compound based on Nylon 66 resin containing 30% Glass Fiber. Added features of this material include: Easy Molding, Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1430	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	100500	kgf/cm ²	ASTM D 638
Flexural Stress	2100	kgf/cm ²	ASTM D 790
Flexural Modulus	75900	kgf/cm ²	ASTM D 790
Tensile Stress, break	140	MPa	ISO 527
Tensile Strain, break	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	9400	MPa	ISO 527
Flexural Stress	217	MPa	ISO 178
Flexural Modulus	8900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	74	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	8	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	82	cm-kgf	ASTM D 3763
Multiaxial Impact	25	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	46	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	252	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	230	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.97E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.47E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.69E-05	1/°C	ISO 11359-2



LNP™ THERMOCOMP™ Compound RF006ESZ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, xflow	7.46E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	222	°C	ISO 75/Af
PHYSICAL			
Density	1.4	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.87	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 1.1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.29	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1	%	ISO 294
Density	1.39	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.07	%	ISO 62
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



LNP™ THERMOCOMP™ Compound RF006ESZ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm