



LNP™ THERMOCOMP™ Compound RFB66

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-100-12 MG

Product reorder name: RFB66

LNP THERMOCOMP RFB66 is a compound based on Nylon 66 resin containing 30% Glass Fiber, 30% Glass Bead.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1540	kgf/cm ²	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	1400	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	1400	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.7	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.8	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	152700	kgf/cm ²	ASTM D 638
Flexural Stress	2530	kgf/cm ²	ASTM D 790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	2260	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2250	kgf/cm ²	ASTM D 790
Flexural Modulus	140600	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	132500	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	128	MPa	ISO 527
Tensile Stress, break, 5 mm/min	122	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.7	%	ISO 527
Tensile Strain, break, 5 mm/min	1.7	%	ISO 527
Tensile Modulus, 1 mm/min	13360	MPa	ISO 527
Flexural Stress	209	MPa	ISO 178
Flexural Modulus, 2 mm/min	12570	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	54	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	6	cm-kgf/cm	ASTM D 256



LNP™ THERMOCOMP™ Compound RFB66

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Multiaxial Impact	42	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	107	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	36	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	257	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	244	°C	ASTM D 648
CTE, -30°C to 30°C, flow	3.5E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	5.1E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	249	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	232	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.7	-	ASTM D 792
Density	1.69	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.34	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.4 - 0.7	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 2	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.51	%	ISO 62



LNP™ THERMOCOMP™ Compound RFB66

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm