



LNP™ THERMOCOMP™ Compound RF00AS

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-100-10 HS

Product reorder name: RF00AS

LNP THERMOCOMP™ RF00AS is a compound based on Nylon 66 resin containing 50% Glass Fiber. Added features of this material include: Heat Stabilized.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	2010	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	179900	kgf/cm ²	ASTM D 638
Flexural Stress	3180	kgf/cm ²	ASTM D 790
Flexural Modulus	127900	kgf/cm ²	ASTM D 790
Tensile Stress, break	194	MPa	ISO 527
Tensile Strain, break	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	14000	MPa	ISO 527
Flexural Stress	300	MPa	ISO 178
Flexural Modulus	14500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	161	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	15	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	124	cm-kgf	ASTM D 3763
Multiaxial Impact	39	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	65	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	252	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.7E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.32E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.81E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.42E-05	1/°C	ISO 11359-2



LNP™ THERMOCOMP™ Compound RF00AS

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	>240	°C	ISO 75/Af
PHYSICAL			
Density	1.573	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.4	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.2	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.34	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.21	%	ISO 294
Density	1.56	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.74	%	ISO 62
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



LNP™ THERMOCOMP™ Compound RF00AS

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm