



LNP™ VERTON™ Compound RV008E

Americas: COMMERCIAL

Also known as: LNP™ VERTON™ Compound RF-7008 EM

Product reorder name: RV008E

LNP VERTON RV008E is a compound based on Nylon 66 resin containing 40% Long Glass Fiber. Added features of this material include: Easy Molding, Structural.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1750	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	142700	kgf/cm ²	ASTM D 638
Flexural Stress	2240	kgf/cm ²	ASTM D 790
Flexural Modulus	118600	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	54	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	237	°C	ASTM D 648
PHYSICAL			
Density	1.47	g/cm ³	ASTM D 792



LNP™ VERTON™ Compound RV008E

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	290 - 305	°C
Front - Zone 3 Temperature	290 - 300	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	280 - 295	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm