



LNP™ VERTON™ Compound RV008ES

Americas: COMMERCIAL

Also known as: LNP™ VERTON™ Compound RF-7008 EM HS

Product reorder name: RV008ES

LNP VERTON RV008ES is a compound based on Nylon 66 resin containing 40% Long Glass Fiber. Added features of this material include: Easy Molding, Heat Stabilized, Structural.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	2170	kgf/cm ²	ASTM D 638
Tensile Stress, break	2170	kgf/cm ²	ASTM D 638
Tensile Strain, yield	1.9	%	ASTM D 638
Tensile Strain, break	1.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	140600	kgf/cm ²	ASTM D 638
Flexural Stress	3090	kgf/cm ²	ASTM D 790
Flexural Modulus	119500	kgf/cm ²	ASTM D 790
Tensile Stress, yield	207	MPa	ISO 527
Tensile Stress, break	206	MPa	ISO 527
Tensile Strain, yield	2	%	ISO 527
Tensile Strain, break	1.9	%	ISO 527
Tensile Modulus, 1 mm/min	13210	MPa	ISO 527
Flexural Stress	301	MPa	ISO 178
Flexural Modulus	12000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	125	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	21	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	87	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	252	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	247	°C	ASTM D 648



LNP™ VERTON™ Compound RV008ES

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	6.12E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.7E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.2E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.7E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	255	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	250	°C	ISO 75/Af
PHYSICAL			
Density	1.48	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.7	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.29	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.69	%	ISO 294
Density	1.47	g/cm ³	ISO 1183



LNP™ VERTON™ Compound RV008ES

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	290 - 305	°C
Front - Zone 3 Temperature	290 - 300	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	280 - 295	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm