



LNP™ THERMOTUF™ Compound RF002I

Americas: COMMERCIAL

Also known as: LNP™ THERMOTUF™ Compound RF-1002 HI

Product reorder name: RF002I

LNP THERMOTUF™ RF002I is a compound based on Nylon 66 resin containing 10% Glass Fiber. Added features of this material include: High Impact.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1090	kgf/cm ²	ASTM D 638
Tensile Strain, break	4.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	49200	kgf/cm ²	ASTM D 638
Flexural Stress	1610	kgf/cm ²	ASTM D 790
Flexural Modulus	44200	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	76	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	6	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	204	°C	ASTM D 648
PHYSICAL			
Density	1.2	g/cm ³	ASTM D 792



LNP™ THERMOTUF™ Compound RF002I

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm