



## LNP™ VERTON™ Compound RVL28

### Americas: COMMERCIAL

Also known as: LNP™ VERTON™ Compound RFL-8028 EM HS

Product reorder name: RVL28

LNP VERTON RVL28 is a compound based on Nylon 66 resin containing 40% Long Glass Fiber, 10% PTFE. Added features of this material include: Easy Molding, Heat Stabilized, Wear Resistant, Structural.

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	Unit	Standard
<b>MECHANICAL</b>			
Tensile Stress, yield	2390	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Stress, break	2390	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Strain, yield	2.3	%	ASTM D 638
Tensile Strain, break	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	147600	kgf/cm <sup>2</sup>	ASTM D 638
Flexural Stress	3440	kgf/cm <sup>2</sup>	ASTM D 790
Flexural Modulus	126500	kgf/cm <sup>2</sup>	ASTM D 790
Tensile Stress, yield	228	MPa	ISO 527
Tensile Stress, break	228	MPa	ISO 527
Tensile Strain, yield	2.4	%	ISO 527
Tensile Strain, break	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	13230	MPa	ISO 527
Flexural Stress	351	MPa	ISO 178
Flexural Modulus	13000	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	143	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	26	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	148	cm-kgf	ASTM D 3763
Multiaxial Impact	77	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	93	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	23	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	256	°C	ASTM D 648



## LNP™ VERTON™ Compound RVL28

### Americas: COMMERCIAL

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	Unit	Standard
<b>THERMAL</b>			
HDT, 1.82 MPa, 3.2mm, unannealed	253	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.86E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	2.16E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.9E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.1E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	255	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	259	°C	ISO 75/Af
<b>PHYSICAL</b>			
Density	1.58	g/cm <sup>3</sup>	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.5	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.7 - 0.9	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.33	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.77	%	ISO 294
Density	1.57	g/cm <sup>3</sup>	ISO 1183



## LNP™ VERTON™ Compound RVL28

### Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
<b>Injection Molding</b>		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	290 - 305	°C
Front - Zone 3 Temperature	290 - 300	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	280 - 295	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm