



LNP™ VERTON™ Compound RV00AE

Americas: COMMERCIAL

Also known as: LNP™ VERTON™ Compound RF-700-10-EM

Product reorder name: RV00AE

LNP VERTON RV00AE is a compound based on Nylon 66 containing 50% Long Glass Fiber. Added features of this grade include: Easy Molding, Structural.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	2230	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	159600	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	3690	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	3660	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	134600	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	216	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.3	%	ISO 527
Tensile Modulus, 1 mm/min	14450	MPa	ISO 527
Flexural Stress	342	MPa	ISO 178
Flexural Modulus, 2 mm/min	13310	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	128	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	39	cm-kgf/cm	ASTM D 256
Multiaxial Impact	84	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	158	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	83	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	42	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	226	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	223	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.98E+01	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.47E+01	1/°C	ASTM D 696



LNP™ VERTON™ Compound RV00AE

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	224	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	222	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.59	-	ASTM D 792
Density	1.59	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.64	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.1 - 0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.4 - 0.6	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	1.2	%	ISO 62



LNP™ VERTON™ Compound RV00AE

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	290 - 305	°C
Front - Zone 3 Temperature	290 - 300	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	280 - 295	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm