



LNP™ THERMOCOMP™ Compound RZ0069

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound RF-1006 FR M

Product reorder name: RZ0069

LNP THERMOCOMP RZ0069 is a compound based on Nylon 66 resin containing 30% Milled Glass. Added features of this material include: Flame Retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	530	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	53500	kgf/cm ²	ASTM D 638
Flexural Stress	980	kgf/cm ²	ASTM D 790
Flexural Modulus	53100	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	28	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	3	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	145	°C	ASTM D 648
PHYSICAL			
Density	1.57	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	1.2	%	ASTM D 955



LNP™ THERMOCOMP™ Compound RZ0069

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	280 - 305	°C
Front - Zone 3 Temperature	295 - 305	°C
Middle - Zone 2 Temperature	280 - 295	°C
Rear - Zone 1 Temperature	265 - 275	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm