



LNP™ LUBRICOMP™ Compound HAL23
Europe-Africa-Middle East: COMMERCIAL

LNP LUBRICOMP HAL23 is a compound based on PA 11 resin containing Aramid Fiber, PTFE. Added features include: Internally Lubricated.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	45	MPa	ISO 527
Tensile Stress, break, 5 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	17	%	ISO 527
Tensile Modulus, 1 mm/min	1400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	54	MPa	ISO 178
Flexural Modulus, 2 mm/min	1900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.4E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	174	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	72	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	1.1	%	SABIC Method
Density	1.14	g/cm ³	ISO 1183



LNP™ LUBRICOMP™ Compound HAL23
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15	%
Melt Temperature	225 - 260	°C
Front - Zone 3 Temperature	260 - 270	°C
Middle - Zone 2 Temperature	230 - 245	°C
Rear - Zone 1 Temperature	200 - 210	°C
Mold Temperature	45 - 55	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm