



LNP™ LUBRICOMP™ Compound SG004
Europe-Africa-Middle East: COMMERCIAL

LNP LUBRICOMP SG004 is a compound based on PA 12 resin containing Graphite. Added features include: Internally Lubricated.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	43	MPa	ISO 527
Tensile Strain, break, 5 mm/min	6.6	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	66	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	147	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	74	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	1.1	%	SABIC Method
Wear Factor Washer	446	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.41	-	ASTM D 3702 Modified: Manual
Static COF	0.31	-	ASTM D 3702 Modified: Manual
Density	1.14	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.14	%	ISO 62-1



LNP™ LUBRICOMP™ Compound SG004
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.12 - 0.2	%
Melt Temperature	225 - 240	°C
Front - Zone 3 Temperature	225 - 240	°C
Middle - Zone 2 Temperature	220 - 230	°C
Rear - Zone 1 Temperature	215 - 225	°C
Mold Temperature	70 - 80	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm