



LNP™ LUBRICOMP™ Compound QL002

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound QL-4020

Product reorder name: QL002

LNP LUBRICOMP QL002 is a compound based on Nylon 6/10 containing 10% PTFE. Added features of this grade are: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	530	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	27300	kgf/cm ²	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	23100	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	61	MPa	ISO 527
Tensile Strain, break, 5 mm/min	4.5	%	ISO 527
Tensile Modulus, 1 mm/min	2480	MPa	ISO 527
Flexural Stress	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	2040	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	40	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	3	cm-kgf/cm	ASTM D 256
Multiaxial Impact	9	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	34	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	42	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	164	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	63	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.12E+02	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	1.15E+02	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	143	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	54	°C	ISO 75/Af



LNP™ LUBRICOMP™ Compound QL002

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Specific Gravity	1.15	-	ASTM D 792
Density	1.14	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.26	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.9 - 3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 4	%	ASTM D 955
Wear Factor Washer	35	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Wear Factor Ring	0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.38	-	ASTM D 3702 Modified
Static COF	0.25	-	ASTM D 3702 Modified
Moisture Absorption (23°C / 50% RH)	0.38	%	ISO 62



LNP™ LUBRICOMP™ Compound QL002

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.12 - 0.2	%
Melt Temperature	270 - 275	°C
Front - Zone 3 Temperature	270 - 280	°C
Middle - Zone 2 Temperature	260 - 270	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm