



LNP™ THERMOCOMP™ Compound IX04513C

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound PDX-I-04513 CCS

Product reorder name: IX04513C

LNP THERMOCOMP™ IX04513C is a compound based on Nylon 6/12 resin containing Glass Fiber. Added features of this material include: Clean Compounding System.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1330	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	90100	kgf/cm ²	ASTM D 638
Flexural Stress	2080	kgf/cm ²	ASTM D 790
Flexural Modulus	82300	kgf/cm ²	ASTM D 790
Tensile Stress, break	128	MPa	ISO 527
Tensile Strain, break	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	8290	MPa	ISO 527
Flexural Stress	187	MPa	ISO 178
Flexural Modulus	7110	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	70	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	104	cm-kgf	ASTM D 3763
Multiaxial Impact	31	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	41	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	197	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.14E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.32E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.04E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.33E-05	1/°C	ISO 11359-2



LNP™ THERMOCOMP™ Compound IX04513C

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	192	°C	ISO 75/Af
PHYSICAL			
Density	1.301	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.15	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 1.1	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.9 - 1.1	%	ISO 294
Density	1.29	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.21	%	ISO 62



LNP™ THERMOCOMP™ Compound IX04513C

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.12 - 0.2	%
Melt Temperature	270 - 275	°C
Front - Zone 3 Temperature	270 - 280	°C
Middle - Zone 2 Temperature	260 - 270	°C
Rear - Zone 1 Temperature	255 - 265	°C
Mold Temperature	65 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm