

# SABIC® LDPE POWDER 1922P9

### LOW DENSITY POLYETHYLENE

## **DESCRIPTION**

SABIC<sup>®</sup> LDPE Powder 1922P9 is an additive free CTR<sup>®</sup> tubular grade with a typically high purity and as such a fine material for masterbatches in film applications.

#### Application

SABIC<sup>®</sup> LDPE Powder 1922P9 is a normal sized powder grade. Since the grade is supplied in powder form it is typically used for pre mixing. The flow and dispersion of pigments and additives that tend towards blocking are typically improved by adding this grade.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190 °C and 2.16 kg	22	dg/min	ISO 1133
Density	919	kg/m³	ASTM D1505
Bulk Density	330	kg/m³	ISO 60
Dry flow	25	sec	ISO 6186
Particle size powder	<900	μm	ASTM D1921
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 10 N (VST/A)	83	°C	ISO 306
DSC test			
enthalpy change	104	J/g	DIN 53765
melting point	107	°C	DIN 53765

## STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.