

# SABIC® LDPE 2501NOW

## LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® LDPE 2501NOW is a grade without additives with a low gel level, which combines good draw down ability with fair optical properties and stiffness.

#### Application

SABIC® LDPE 2501NOW is typically used in diaper film, surface protection film, lamination film and in applications where low blocking behavior is required and the presence of slip and anti block is unwanted.

SABIC® LDPE 2501NOW can typically be used for food applications due to very low migration levels.

#### Film properties

Film properties have been measured at film of 50 µm with a BUR of 3.

The film has been produced on Kiefel IBC blown film line with 200 kg/h. Die size 200 mm, die gap 0.8 mm.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>PHYSICAL</b>			
Density	925	g/cm <sup>3</sup>	ISO 1183
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	0.75	dg/min	ISO 1133
<b>OPTICAL PROPERTIES</b>			
Haze	10	%	ASTM D1003
Clarity	25	mV	SABIC method
<b>FILM PROPERTIES</b>			
Impact strength	15	kJ/m	ASTM D4272
Tear strength TD	45	kN/m	ISO 6383-2
Tear strength MD	45	kN/m	ISO 6383-2
<b>Tensile test film</b>			
Yield stress TD	12	MPa	ASTM D882
Stress at break TD	20	MPa	ASTM D882
Modulus of elasticity TD	200	MPa	ASTM D882
Stress at break MD	25	MPa	ASTM D882
<b>Tensile test film</b>			
Strain at break MD	>200	%	ASTM D882
Strain at break TD	>500	%	ASTM D882
Coefficient of friction	0.9	-	ASTM D1894
Blocking	20	g	SABIC method
Re-blocking	<5	g	SABIC method
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
at 10 N (VST/A)	98	°C	ISO 306