

SABIC[®] LDPE POWDER 2102P5

LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC[®] LDPE Powder 2102P5 is an additive free standard CTR[®] tubular grade for masterbatch with a relatively low melt flow rate. This grade is supplied in powder form.

Application

SABIC[®] LDPE Powder 2102P5 is a general medium sized powder grade, typical used for textile coating, carpet backing and compounding applications with a low viscosity. Further it can be used for low filled or additive masterbatches (e.g. slip agents, anti fog agents, anti static agents, thermal stabilizers).

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190 °C and 2.16 kg	1.9	dg/min	ISO 1133
Density	921	kg/m³	ASTM D1505
Bulk Density			
Method B	340	kg/m³	ASTM D1895
Dry flow	23	sec	ISO 6186
Particle size powder	<600	μm	ASTM D1921
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 10 N (VST/A)	91	°C	ISO 306
DSC test			
melting point	109	°C	SABIC method
enthalpy change	110	J/g	SABIC method

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC.com). Additional specific information can be requested via your local Sales Office.

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.