

### **POLYMERS**

# SABIC®HDPE Blown Film F01552

# **PRODUCT DESCRIPTION**

F01552 is a high molecular weight, high density polyethylene copolymer which has a broad molecular weight distribution. The design of the product, molecular architecture and density, gives it a unique combination of easy extrusion with high film strength and drawdown capability.

# **TYPICAL APPLICATIONS**

F01552 is recommended for blown film extrusion. This product is suggested for the manufacture of strong strength millinery and notion bags, deep freezer bags, table cloths and thin film as quality replacement for papers products.

### **TYPICAL DATA**

PROPERTIES	Unit	Value (1)	Test Method
Melt Flow Rate			
@ 190°C & 2.16 kg load	g/10 min	0.15	ASTM D 1238
@ 190°C & 21.6 kg load		16	
Density @ 23°C	Kg/m³	952	ASTM D 1505
MECHANICAL PROPERTIES (2)			
Tensile Strength @ break, MD, TD	MPa	55,49	ASTM D 882
Tensile Elongation @ break, MD, TD	%	400,610	ASTM D 882
Tensile Strength @ yield, MD, TD	MPa	31,30	ASTM D 882
1% Secant Modulus, MD, TD	MPa	1400,1700	ASTM D 882
Dart Impact Strength	g	180	ASTM D 1709
Elmendorf Tear Strength, MD, TD	g	4,40	ASTM D 1922
THERMAL PROPERTIES			
Vicat Softening Point	°C	125	ASTM D 1525

(1) Typical values: not to be construed as specification limits.

(2) Properties are based on 15 µm film produced at 4 BUR using 100% F01552.